

ALPHA – MARITEX *STYLE 2025/9383*

DESCRIPTION

Alpha Maritex Style 2025/9383 meets the requirements of Coast Guard Specification 164.009 for fire-retardant material and is included in Military Specification MIL-C-20079H, Type 1, Class 9. It can meet Military Specification MIL-I-24244B and is ANSI/FM 4950 approved for welding curtains.

APPLICATIONS

Alpha Maritex Style 2025/9383 has been specifically designed as a jacketing or lagging material for use over insulated surfaces. It is also widely used for the fabrication of removable/reusable insualtion blankets on turbines, fittings, flanges and valves.

ADVANTAGES

Alpha Maritex Style 2025/9383 is finished with treatment #9383 to set the weave and reduce fraying when cut. The finish also removes a large percentage of organic binders on the fabric to enhance handling and weave setting characteristics. Other finishes and coatings are available including Hypalon, Neoprene and silicone.

*This lagging fabric is available red dyed to comply with Federal Standard 595A color chip 31158.

PROPERTY DATA STYLE 2025/9383

CHARACTERISTIC METHOD			<u>VALUES</u> *			
			<u>ENGLISH</u>		<u>METRIC</u>	
WEIGHT	ASTM-D-37	ASTM-D-3776		0%	605.2 g/m² ± 10%	
THICKNESS ASTM-D-17		7 0.030" ± 10%		0.762 mm ± .025 mm		
TENSILE STRENGTH	ASTM-D-579	ASTM-D-579		250 lbs/inch	44.72 kg/cm	
			Fill-	200 lbs/inch	35.72 kg/cm	
FLAME RESISTANCE	ASTM D-642	13	Char Length	1 inch max.	2.54 cm max.	
			Afterglow	1 second max.	1 second max.	
			Flame Out	1 second max.	1 second max.	
TEMPERATURE RESISTAN	CE Service Tem	Service Temperature			+538 °C	
ENDS PER INCH	ASTM-D-37	75	20 (±2) x 14 (±	2)		
WIDTHS	ROLL LENGTH	WEIGHT	/ ROLL			
36" (91.44 cm)	50 YD.(45.72 m)	61 lbs (2	7.67 kg)			
48" (121.9 cm)	50 YD	90 lbs (4	0.82 kg)			
60" (152.4 cm)	50 YD	114 lbs (5	1.71 kg)			

DATA SHEET: 12683 FM REV: F DATE: 4/21/2017 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.