



# ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701  
**T:** 732.634.5700 **F:** 732.634.1430 alphainc.com

ALPHA - MARITEX  
 STYLE 3201-2-CMTS

DESCRIPTION

Alpha Maritex Style 3201-2-CMTS is a fiberglass fabric coated with a specially formulated silicone rubber designed to meet the rigid requirements for use in nuclear reactors. This special high temperature, flame retardant silicone rubber provides greater life and improves resistance to abrasion flexing, tear and puncture.

ADVANTAGES

Low Smoke, Water and Oil Resistant, Can be easily sewn, Flame Retardant, Lightweight, Chemical Resistant, Easy to Fabricate.

APPLICATIONS

Removable Insulation Blankets, Expansion Joints, Welding Curtains, Equipment Covers, Flange Covers, Safety Clothing. This product is designed specifically for high temperature (500 °F) removable blankets, and flange and valve covers where a very soft and flexible fabric is desired or needed.

PROPERTY DATA  
 STYLE 3201-2-CMTS

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	17.0 oz/sy ± 10%	578 g/m <sup>2</sup> ± 10%
THICKNESS	ASTM-D-1777	0.015" ± .001"	0.381 mm ± .025 mm
TENSILE STRENGTH	ASTM-D-5035	Warp- 300 lbs./inch Fill- 225 lbs/inch	53.58 kg/cm 40.19 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp- 50 lbs. Fill- 50 lbs.	22.68 kg 22.68 kg
BURST STRENGTH	ASTM-D-3786	600 psi	42 kg/cm <sup>2</sup>
FLAME RESISTANCE	ASTM-D-6413	Char Length 0.3 inches max. Afterglow 1 sec. max Flame Out 1 sec. max	0.762 cm max. 1 sec. max 1 sec. max
TEMPERATURE RESISTANCE		Cold: -65 °F, Hot: 500 °F Inter.: 700 °F	-54 °C to 260 °C, Inter.: 371 °C
COLOR and COATING		Mocha Tan Silicone	
BASE FABRIC and WEAVE		Fiberglass/Plain Weave	

DATA SHEET: 14001 REV: A DATE: 4/20/09 \*All values are nominal unless otherwise specified.

**Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.